








Caratteristiche tecniche / Technical features

	CARATTERISTICHE TECNICHE TECHNICAL DATA	ISO NORME ISO NORMS	VALORE PRESCRITTO DALLE NORME VALUES REQUIRED BY THE NORMS	VALORI VALPANARO VALUE VALPANARO
	Assorbimento % d'acqua Water absorption %	ISO 10545-3 ASTM C-373	≤ 0,05%	Conforme Conforming
	Resistenza alla flessione Breaking strenght	ISO 10545-4 ASTM C-648	≥ 35 N/mm ²	Conforme Conforming
	Resistenza al gelo Frost resistance	ISO 10545-12 ASTM C-1026	Richiesta Required	Non gelivo Frost proof
	Resistenza all'attacco chimico Chemical resistance	ISO 10545-13 ASTM C-650	Secondo la classificazione riportata dal fabbricante Metodo di prova disponibile GB min/min UB According to the classification stated by the manufactured Testing method available GB min/min UB	Conforme Conforming
	Resistenza allo scivolamento Slip resistance (coefficient of friction)	DIN 51130	R10	Conforme Conforming
		ASTM C-1028	> 0,60 dry > 0,70 wet	
	Resistenza agli sbalzi termici Thermal shock resistance	ISO 10545-9	Metodo di prova effettuabile Test method available	Resistenti Resistant
	Resistenza alle macchie Stain resistance	ISO 10545-14	Classi ≥ 3	5

Imballi / Packaging

FORMATO SIZE	SPESS. THICKN.	PZ/BOX	M ² /BOX	KG/BOX	BOX/ PALLET	M ² / PALLET	KG/ PALLET
60x60 (24"x24")	9,5 mm	3	1,08	25,55	40	43,20	1020
30x60 (12"x24")	9,5 mm	6	1,08	21,50	40	43,20	873
45x45 (18"x18")	9,5 mm	7	1,42	25,00	52	73,84	1316
30x30 (12"x12") mosaico 16	9,5 mm	11	0,99	18,00	36	35,64	-
30x30 (12"x12") mosaico 64	9,5 mm	10	0,92	18,00	36	33,12	-
7,5x60 (3"x24") battiscopa	-	20	12Ml	17 KG/BOX	-	-	-

ceramiche
CandiaVALPANARO

ABM ITALY SPA

Uffici e showroom - Offices and showroom

Via Radici in Piano nr 1

41042 Fiorano Modenese (MO) - Italy

Tel +39 0536-076545 - Fax +39 0536-076546

commerciale@abm-italia.it

info@abm-italia.it

www.candiavalpanaro.it

