











Plant

Caratteristiche/Features/Caracteristiques/Eigenschaften/Eigenschappen/Características Gres Fine Porcellanato – EN 14411 ISO 13006 Gruppo Bla Annex G

		Regulation	Required standards	Refin values	
	Dimensioni/Sizes/Dimensions/ Abmessungen/Afmetingen/ Dimensiones	UNI EN ISO 10545/2	→ Lunghezza e larghezza/Length and width/Longueur et largeur/ Länge und Breite/Länge en breedte/Longitud y anchura → Spessore/Thickness/Épaisseur/Stärke/Dikte/Dorsor → Rettineità spigoli/Linearity/Rectitude des arêtes/ Kantengeradheit/Rechtheid kanten/Rectitud de los lados → Ortogonalità/Wedging/Orthogonalité/Rechtwinkligkeit/ Haakheid hoeken/Ortogonalidad → Planarità/Warpage/Planéité/Ebenflächigkeit/Vlakheid/ Planitud	± 0,6 % max. ± 5 % max. ± 0,5 % max. ± 0,5 % max. ± 0,5 % max.	Conforme/Compliant/ Conforme/Entspricht/ Conform/Conforme
	Assorbimento acqua/Water absorption/ Absorption d'eau/Wasseraufnahme/ Waterabsorptie/Absorción de agua	UNI EN ISO 10545/3	≤ 0,5 %	0,2 %	
	Resistenza alla flessione/Flexual Strenght/ Résistance à la flexion/Biegezugfestigkeit/ Buigvastheid/Resistencia a la flexión	UNI EN ISO 10545/4	≥ 35 N/mm ²		Conforme/Compliant/ Conforme/Entspricht/ Conform/Conforme
	Resistenza all'abrasione profonda/Deep abrasion resistance/Resistance à l'abrasion/Bestimmung des Widerstandes gegen Tiefenverschleiß/ Weerstand tegen afschuren/Resistencia a la abrasión profunda	UNI EN ISO 10545/6	≤ 175 mm ³		Conforme/Compliant/ Conforme/Entspricht/ Conform/Conforme
	Resistenza agli sbalzi termici/ Thermal shock resistance/Resistance aux écarts de température/ Temperaturwechselbeständigkeit/ Temperatuurswisselingen/Resistencia al choque térmico	UNI EN ISO 10545/9	Nessun campione deve presentare difetti visibili/ No sample must show visible defects/ Aucun échantillon ne doit présenter des défauts visibles/ Kein Exemplar darf sichtbare Schäden aufweisen/ Geen enkel monster mag zichtbare gebreken vertonen/ Ninguna muestra debe presentar defectos visibles		Conforme/Compliant/ Conforme/Entspricht/ Conform/Conforme
	Resistenza al gelo/Frost resistance/Résistance au gel/Frostwiderständigkeit/Vorstbestandheid/ Resistencia a la helada	UNI EN ISO 10545/12	Resistent/Resistant/ Résistants/Widerstandsfähig/ Weerbaar/Resistentes		Conforme/Compliant/ Conforme/Entspricht/ Conform/Conforme
	Resistenza all'attacco chimico/Chemical resistance/Resistance à l'attaque/Chimique/ Beständigkeit gegen Chemikalien/Chemische bestandheid/Resistencia al ataque químico	UNI EN ISO 10545/13			Conforme/Compliant/ Conforme/Entspricht/ Conform/Conforme
	Resistenza alle macchie/Stain resistance/ Insensibilité aux taches/Widerstandsfähigkeit gegen fl eckenbildende/Substanzen/Weerstand tegen vlekken/Resistencia a las manchas	UNI EN ISO 10545/14	UGL	Metodo di prova disponibile/Tests method available/ Methode d'essai disponible/Verfügbares Prüfverfahren/ testmethode beschikbaar/Método de prueba disponible	Conforme/Compliant/ Conforme/Entspricht/ Conform/Conforme
	Indicazione di resistenza allo scivolamento/ Assesment of slip resistance/Indication de la résistance au glissement/ Bestimmung der Trittsicherheit/Indicatie voor de slipvastheid/ Indicación de resistencia al deslizamiento	EN51130	R		R10
	Coefficiente di attrito dinamico/Measurement of dynamic friction coefficient/Mesure du coefficient de frottement dynamique/Messung des Dynamischen Reibungskoeffizienten/Meting van de dynamische wrijvingscoefficient/Coefficiente de rozamiento dinámico	BCRA BOT 3000	> 0,40 > 0,42		Dry 0,88 Wet 0,74 0,51